




SPACEREFLEX®
FÁBRICA DE ISOLAMENTO TERMO-ACÚSTICO
FACTORY OF THERMO-ACOUSTIC INSULATION

SOMOS FABRICANTES
WE ARE MANUFACTURES
NOUS SOMMES FABRICANTS

TECHNICAL SPECIFICATIONS





Technical Data

- | | |
|--------------------------------------|---|
| • Thickness | 4 mm |
| • Weight | 197 (Gr. /M2) |
| • Density (NP EN 1602) | 20 Kg/M ³ (± 3Kg/M ³) |
| • Rupture Resistance (NP ISO1798) | Longitudinal = 8,32 Mpa
Transversal = 0,26 Mpa |
| • Compression Deflection (NP EN 826) | 10% = 4,95 kPa
25% = 10,44 kPa |
| • Impermeability (ASTM 96/94) | 0% |
| • Thermal conductivity (ISO8301) | 0,037 (W/m.K) |

Applications

- Construction / Rehabilitation of buildings;
- Modular Construction – Wood, LSF (Light Steel Framing);
- Packaging (Thermal Boxes / Containers).



Equivalent, Thermal Conductivity:

- Rockwool 30mm
- Glass Wool 30mm
- Expanded Polystyrene 30mm
- Extruded Polystyrene 30mm

SECTOR:

- ✓ Residential
- ✓ Commercial
- ✓ Industry

Increase energy savings

Use SPACE REFLEX insulation!

Acoustic Insulation

Ref.	Length x Width	Area	Ø
F52A	50m x 1,20m	60m ²	± 57 cm

COMPOSITION

Formed by a polyethylene foam layer, laminated on the outer faces with aluminum film.

Benefits:

- Quick and easy to install;
- Easy to handle;
- Lightweight and flexible;
- Does not require special tools, equipment or any kind of special clothing;
- Do not harmful to human health;
- Reduced thickness.

FÁBRICA / FACTORY
AV. DRA. ASSUNÇÃO VASCONCELOS CHAVES, LOTE C1
DUME - APARTADO 2603
4701-907 BRAGA - PORTUGAL

T +351 253 331 065
F +351 253 331 066
E INFO@SPACEREFLEX.COM
W WWW.SPACEREFLEX.COM

