



SPACEREFLEX®
FÁBRICA DE ISOLAMENTO TERMO-ACÚSTICO
FACTORY OF THERMO-ACOUSTIC INSULATION

SOMOS FABRICANTES
WE ARE MANUFACTURERS
NOUS SOMMES FABRICANTS

TECHNICAL SPECIFICATIONS



Technical Data

- | | |
|---|--------------|
| • Total Thickness | 0,091 mm |
| • Power Grip to Steel | 12,5 N/25mm |
| • Traction MD | 105 N/25mm |
| • Stretching | 30 % |
| • Temperature Range | -20°C a 80°C |
| • Maximum Temperature (Short Time Period) | 100°C |

Applications

- Insulation Joints;
- Joints against Vapor and Condensation;
- HVAC ducts;
- Flues;
- Exhaust hose (ex.: heaters);
- Automotive Pipe Joints;
- Etc.

SECTOR:

- ✓ Residential
- ✓ Commercial
- ✓ Industry
- ✓ Automobile

Increase energy savings

Use SPACE REFLEX insulation!

SR ALUMINIUM TAPE

Ref.	Width x Length	Area	Ø
FT03	50mm x 50	36 Rls	± 11,2cm
FT04	75mm x 50	16 Rls	± 11,2cm

COMPOSITION

Aluminum sheet with Acrylic Adhesive Paper with silicone protection.

Note: The tape should be stored in a clean, dry place at a temperature of approximately 23 ° C and a relative humidity of 50 %.

SPACE REFLEX® recommends special attention to the contact surfaces being clean, without dust, oils, or any other non-stick substance.

The technical data contained in this Technical guidance only have information character for the End User, and does not imply any legal guarantee to certain properties, as there are numerous influences that may occur during handling and use of the product.

FÁBRICA / FACTORY

AV. DRA. ASSUNÇÃO VASCONCELOS CHAVES, LOTE C1
DUME - APARTADO 2603
4701-907 BRAGA - PORTUGAL

T +351 253 331 065

F +351 253 331 066

E INFO@SPACEREFLEX.COM

W WWW.SPACEREFLEX.COM

